Glycothermal Synthesis and Characterization of 3Y-TZP Nanoparticles

Jeong-Hwan Song[†] and Ju-Hee Lee*

Department of Information & Electronic Materials Engineering, PaiChai University, Daejeon 302-735, KOREA

*Department of Dental Laboratory Technology, Daejeon Health Sciences College, Daejeon 300-711, KOREA

(Received June 30, 2009 : Received in revised form July 22, 2009 : Accepted August 3, 2009)

Abstract In this study, 3 mol% yttria-tetragonal zirconia polycrystal (3Y-TZP) nanoparticles were synthesized by the glycothermal method under various reaction temperatures and times. The co-precipitated precursor of 3Y-TZP was prepared by adding NH_4OH to starting solutions, and then the mixtures were placed in an autoclave reactor. Tetragonal yttria-doped zirconia nanoparticles were afforded through a glycothermal reaction at a temperature as low as 220 °C, using co-precipitated gels of ZrCl_4 and $\text{YCl}_3 \cdot 6\text{H}_2\text{O}$ as precursors and 1,4-butanediol as the solvent. The synthesized 3Y-TZP particles were characterized by X-ray diffraction (XRD), field emission scanning electron microscopy (FESEM), transmission electron microscopy (TEM), and Raman spectroscopy. The 3Y-TZP particles have a stable tetragonal phase only at glycothermal temperatures above 200 °C. To investigate phase transition, the 3Y-TZP particles were heat treated from 400 to 1400 °C for 2 h. Raman analysis indicated that, after heat treatment, the tetragonal phase of the 3Y-TZP particles remained stable. The results of this study, therefore, suggest that 3Y-TZP powders can be prepared by the glycothermal method.

Key words 3Y-TZP, nanoparticle, glycothermal, 1,4-butanediol, Raman.

1. Introduction

Zirconia ceramics show considerable potential for use in structural and functional applications due to their excellent mechanical, electrical, thermal, and optical properties.¹⁾ Yttria-stabilized tetragonal zirconia polycrystal (Y-TZP) has attracted much attention as a promising structural material due to its excellent fracture toughness and high strength in applications such as cutting tools, valve guides, extrusion dies, grinding media, etc.^{2,3)} Yttria-stabilized cubic zirconia (Y-CSZ) can be considered a candidate for a solid-electrolyte material in ceramic fuel cells because of its excellent oxygen-ion conductivity.^{4,5)} Furthermore, zirconia-based materials have become increasingly important in all-ceramic dental restorations due to their favorable esthetics and their outstanding biological compatibility and transparency.

Pure zirconia has three polymorphisms at atmospheric pressure : monoclinic (from room temperature up to 1170 °C), tetragonal (1170-2370 °C), and cubic (2370 °C and above).^{2,6)} The tetragonal to monoclinic phase transformation is associated with a volume expansion of approximately 3-4%, with cracks arising from the sintering temperature during

cooling. To inhibit these phase transformations, several aliovalent oxides such as CaO, MgO, CeO₂, or Y₂O₃ are added; these oxides allow the stabilization of the cubic or tetragonal phases at room temperature.^{7,8)} TZP materials are extensively used for dental restorations in the biomedical field because of their excellent mechanical properties, especially when 3 mol% yttria is used as the stabilizer dopant.

The synthesis of nanocrystalline particles has been considered extremely important in the improvement of the mechanical and chemical properties of zirconia-based materials.⁹⁾ Various wet chemical methods, such as sol-gel synthesis,¹⁰⁾ polymeric precursor route,¹¹⁾ combustion synthesis,¹²⁾ hydrothermal treatment,¹³⁾ and co-precipitation from metal aqueous solutions¹⁴⁾ have been explored for the preparation of diverse doped zirconia powders due to the impressive chemical/physical homogeneity and good sinterability of the products. Only a few studies have investigated the use of glycol media and the glycothermal method to synthesize crystalline ceramic powders. Previous studies have shown that metal oxide powders can potentially be prepared by glycothermal synthesis in 1,4-butanediol solutions.^{15,16)} Crystalline ceramic powders can directly be prepared by glycothermal synthesis at reaction temperatures and pressures lower than those required by the

[†]Corresponding author
E-Mail : song_jeonghwan@pcu.ac.kr (J. -H. Song)

hydrothermal method. The glycothermal process does not require heat treatment for crystallization and mineralizers for the formation of anhydrous crystalline materials in some cases because 1,4-butanediol can act as an oxidizer. Therefore, this process does not involve contamination by alkalis such as KOH and NaOH, which are commonly used in the conventional hydrothermal method.

In this work, 3Y-TZP nanoparticles were prepared by the glycothermal method. The characteristics of the particles obtained by glycothermal reaction were evaluated by X-ray diffraction (XRD), scanning electron microscopy (SEM), and transmission electron microscopy (TEM). The structural evolutions of the 3Y-TZP nanoparticles after cooling from heat treatment temperature were examined by Raman spectroscopy.

2. Experimental procedure

The process for the preparation of 3 mol% yttria-doped zirconia by glycothermal treatment in a 1,4-butanediol (98.0%, Oriental Chem.) solution is schematically illustrated in Fig. 1. Stoichiometric amounts of ZrCl_4 (99.5%, Aldrich Chemical Co.) and $\text{YCl}_3 \cdot 6\text{H}_2\text{O}$ (99.9%, Aldrich Chemical Co.) were dissolved in 25 ml of CO_2 -free deionized water (ice cold water) to afford an aqueous solution of 1 M ZrCl_4 containing a source of Y. The ice cold water was used because the metal chloride can be readily hydrolyzed by reacting with the water in the air and evolves a Cl_2 gas because of its large vapor pressure at room temper-

ature. This aqueous solution was maintained in a stable state without precipitation at room temperature. Co-precipitated precursors of 3Y-TZP were immediately prepared by drop-wise addition of NH_4OH with $\text{pH} \approx 12$ (28%, DC Chem.) into 25 ml of the starting aqueous solutions with vigorous stirring. The co-precipitated precursor was separated and washed with CO_2 -free deionized water in three cycles for 10-min centrifugation at 10,000 rpm, until no residual Cl^- remained.

The obtaining precursor and 70 ml of 1,4-butanediol solvent were combined in a 100 ml Teflon container, which was then placed in the stainless-steel pressure vessel of the autoclave reactor. The reaction autoclave was then heated to the desired temperature at a rate of $2^\circ\text{C}/\text{min}$. The reaction time at each desired temperature was 6 to 24 h. After glycothermal reaction, the autoclave reactor was cooled to $\sim 40^\circ\text{C}$. The particles were separated and washed with CO_2 -free deionized water and ethanol. After washing, the obtained particles were dried in a 100°C oven for 24 h.

The dried particles were analyzed for phase composition and crystal structure using X-ray diffraction (XRD, $\text{Cu K}\alpha_1$, 30 kV-30 mA, Shimadzu, Japan) over the 2θ range from 20° to 80° at a scan rate of $2^\circ/\text{min}$. The morphology of the synthesized particles was observed using field-emission scanning microscopy (FESEM, Hitachi S4800, Japan) and transmission electron microscopy (TEM, Jeol JEM-2100F, Japan). For each specimen, Raman spectroscopy measurements of the obtained 3Y-TZP particles were performed over the range of $100\text{--}1000\text{ cm}^{-1}$ using an FT Raman spectrometer (Raman, Bruker RFS 100/S, Germany) using an excitation wavelength of 1064 nm from a 100-mW Nd:YAG laser. The main reason for using Raman spectroscopy is that the tetragonal and monoclinic polymorphs of zirconia are reported to have distinct and characteristic Raman spectra.

3. Results and discussion

Fig. 2 presents the XRD results of the obtained powders at various glycothermal conditions for the synthesis of pure 3Y-TZP. The XRD patterns show that the synthesized zirconia powders had a single phase. The precursor derived from co-precipitation is amorphous, as shown in Fig. 2(a). The powders obtained below 180°C for 24 h still show an amorphous state (Figs. 2(b and c)). The crystallization of 3 mol% yttria-doped zirconia powders prepared directly at a reaction temperature of $>200^\circ\text{C}$ for 24 h occurred

Fig. 1. Experimental flowchart for the synthesis of 3Y-TZP powders using the glycothermal method.

Fig. 2. XRD patterns of 3Y-TZP powder obtained by the glycothermal method at various reaction temperatures for 24 h. (a) co-precipitated precursor, (b) at 160 °C, (c) at 180 °C, (d) at 200 °C, and (e) at 220 °C.

without the formation of intermediate phases (Figs. 2(d and e)). Only the crystalline phase was observed corresponding to the tetragonal structure of zirconia (JCPDS card 88-1007). With an increase in the reaction temperature, the intensity of the diffraction peak increases. The powders prepared in short glycothermal reaction times of less than 12 h are amorphous, whereas the powders synthesized at reaction times of >12 h could be crystalline. The lattice parameters of the obtained powder were determined to be $a = 0.361$ nm and $c = 0.517$ nm, using the least square refinement method. This value agreed well with the lattice constant of the tetragonal structure of 3Y-TZP reported in a previous study ($a_t = 0.511$ nm and $c_t = 0.518$ nm).¹⁷⁾

The average crystallite sizes were determined from XRD patterns according to Scherrer's equation:

$$D = \frac{k\lambda}{\beta \cos \theta} \quad (1)$$

where D is the average crystallite size, k is a constant equal to 0.94, θ is the angle (101) of the main peak, λ is the X-ray wavelength equal to 1.5406 Å, and β is the full width at the half peak maximum. The average crystallite size of the 3Y-TZP powders obtained at 220 °C for 24 h was approximately 10.0 nm, as shown in Fig. 2(e).

Fig. 3 shows a photomicrograph of the 3Y-TZP powders taken by FESEM. Although the obtained powder was agglomerated to some extent, it was observed that the particles had a uniform distribution with a size of 20-30 nm

Fig. 3. FESEM photomicrograph of the 3Y-TZP powder obtained by glycothermal reaction at 220 °C for 24 h.

and a spherical polygonal shape. The size of the 3Y-TZP particles prepared by glycothermal synthesis decreased with an increase in the reaction temperature because higher reaction temperatures generally promoted the dehydration reaction on the surface of the co-precipitated precursor.¹⁸⁾

TEM was performed to investigate the primary particle size and morphology. As shown in the TEM images of Fig. 4(a), it is clear that the spherical polygonal morphology of the 3Y-TZP particles prepared by glycothermal reaction at 220 °C for 24 h are well-dispersed; the crystals have a relatively uniform distribution. The primary particles observed by TEM showed an approximate size of 10-15 nm with the average crystallite size value estimated from XRD. The high resolution transmission electron microscopy (HRTEM) image of the inset in Fig. 4(a) shows an enlargement of the area indicated. A tetragonal atomic arrangement is regularly observed with the incident electron beam aligned along the [010] zone axis of 3Y-TZP. The crystallographic array shows an interplanar distance of 0.294 nm as (101) planes of 3Y-TZP.

Fig. 4(b) is a schematic illustration representing the tetragonal structure and atom configuration of 3Y-TZP. The d value ($d = 0.296$ nm) calculated using the lattice constant of the tetragonal structure is very similar to that estimated by analysis of the HRTEM image.

Raman analysis investigated the effect of temperature dependence on the heat treatment of the 3Y-TZP powders prepared at 220 °C for 24 h, as shown Fig. 5. Monoclinic ZrO_2 has a characteristic spectrum with 18 theoretically determined Raman active modes, while tetragonal zirconia has only 6 typical bands of the different Raman modes because of its higher symmetry. The band at 147 cm^{-1} is assigned to (O_t-Zr-O_t) and ($Zr-O_t-Zr$) bending; that at 259 cm^{-1}

Fig. 4. (a) TEM and HRTEM images of the 3Y-TZP powder obtained by glycothermal reaction at 220 °C for 24 h, (b) A schematic illustration of the tetragonal structure and atom configuration.

Fig. 5. Raman spectra with various heat treatment temperatures of the 3Y-TZP powder obtained at 220 °C for 24 h. (a) as-prepared powder, (b) 400 °C, (c) 600 °C, (d) 800 °C, (e) 1000 °C, (f) 1200 °C, and (g) 1400 °C.

to (Zr-O_{II}) bending; and those at 464 and 322 cm⁻¹ to Zr-O_I/O_{II} stretching and to the coupling O_I(or O_{II})-Zr-O_I(or O_{II}). The bands at 606 and 642 cm⁻¹ are also assigned to (Zr-O_I) stretching.¹⁹⁾ In all of the samples, after cooling from each heat treatment temperature, six Raman lines, occurring at 147.9, 265.6, 322.5, 464.2, 608.8, and 641.6 cm⁻¹ could be observed. None of the Raman doublet lines occurring at 180 and 190 cm⁻¹ of the monoclinic phase were observed

in Fig. 5; they were identified with the typical characteristics of the tetragonal phase. These results suggest that the primary crystal phase of the 3 mol% yttria-doped zirconia nanoparticles was the tetragonal phase. The intensity of the Raman spectra increases with the heat treatment temperature because higher temperatures promote crystallinity in the tetragonal phase.

4. Conclusion

Nano-sized 3Y-TZP particles have been synthesized by the glycothermal reaction of co-precipitated precursors from stoichiometric amounts of ZrCl₄ and YCl₃ · 6H₂O under autogenous vapor pressures, with the use of 1,4-butanediol glycol as the solvent. From TEM and XRD analysis, this work shows that nanoparticles were directly obtained in the Y₂O₃-doped ZrO₂ with a stable tetragonal phase at 200 °C for 24 h without morphological change. The average crystallite size of the synthesized 3Y-TZP nanoparticles was approximately 10 nm with a relatively uniform distribution. Furthermore, it was demonstrated that the stabilization of 3Y-TZP particles can be investigated by varying the temperature conditions of the heat treatment from 400 to 1400 °C. The effect of temperature dependence was investigated by Raman analysis. The prepared 3Y-TZP powders were able to maintain a stable tetragonal phase regardless of the heat treatment temperature conditions.

References

1. E.C. Subbara, Science and Technology of Zirconia, Adv. in Ceramics vol.3, p.1-24, eds., A. H. Heuer, L. W. Hobbs (The American Ceramic Society, Columbus, Ohio, 1981).
2. R. C. Garvie, R. H. Hannink and R. T. Pascoe, Nature, **258**, 703 (1975).
3. R. C. Garvie, J. Phys. Chem., **82**, 218 (1978).
4. P. Holtappels and C. Bagger, J. Eur. Ceram. Soc., **22**(1), 41 (2002).
5. I. Zhitomirsky and A. Petric, J. Eur. Ceram. Soc., **20**(12), 2055 (2000).
6. J. Cai, C. Raptis, Y. S. Raptis and E. Anastassaki, Phys. Rev. B, **51**, 201 (1995).
7. C. Piconi and G. Maccauro, Biomaterials, **20**, 1 (1999).
8. D. J. Green, R. H. Hannink and M. V. Swain, Transformation toughening of ceramics. Boca Raton, FL: CRC (1989).
9. T. G. Nieh and J. Wadsworth, Acta Mater., **38**, 1121 (1990).
10. J. Livage, F. Beteille, C. Rouse, M. Chatry and P. Davidson, Acta Mater., **46**, 743 (1998).
11. A. L. Quinelato, E. Longo, L. A. Perazolli and J. A. Varela, J. Eur. Ceram. Soc., **20**, 1077 (2000).
12. R. E. Juarez, D. G. Lamas, G. E. Lascalea and N. E. Walsõe de Reca, J. Eur. Ceram. Soc., **20**, 133 (2000).
13. G. Dell'Agli and G. Mascolo, J. Eur. Ceram. Soc., **20**, 139 (2000).
14. D. Segal, Key Eng. Mater., **153**, 241 (1998).
15. M. Inoue, H. Tanino, Y. Kondo and T. Inui, J. Am. Ceram. Soc., **72** (2), 352 (1989).
16. M. Inoue, J. Phys.: Condens. Matter, **16**, S1291-S1303 (2004).
17. C. Chang and S. Jon, CIMTEC 2002 Proc., **4**, 761 (2002).
18. Y. J. Jung, D. Y. Lim, J. S. Nho, S. B. Cho, R. E. Riman and B. W. Lee, J. Crystal Growth, **274**, 638 (2005).
19. Y. Gogotsi and V. Domnich, in High-Pressure Surface Science and Engineering (Materials Science and Engineering), (CRC Press, Taylor & Francis, 2003) p. 467-520.