

ER11

Microstructure and Magnetic Properties of FePt Films on Anodized Aluminum Oxide Membranes

Shih-Yuan Chen¹, Yeong-Der Yao², and Chin-Chung Yu^{3*}


¹ Materials Science and Engineering, National Tsing Hua University, Hsinchu, Taiwan

² Materials Engineering, Tatung University, Taipei, Taiwan

³ Applied Physics, National University of Kaohsiung, Kaohsiung, Taiwan

*Corresponding author: Chin-Chung Yu, e-mail: M9003505@mail.nust.edu.tw

In pursuit of patterned recording media, magnetic nanomaterials fabricated through porous anodized aluminum oxide (AAO) have been widely investigated [1, 2]. In this study, FePt films were prepared on the AAO membranes with pore diameter of around 20nm and 200nm. In order to prevent the interdiffusion, a 10nm thick Au buffer was grown on AAO templates prior to FePt layers. Detail investigation on the XRD spectrum showed the 20nm pore diameter AAO template can assist the formation of Au (100) phase that resulted in the formation of FePt L₁₀(001) phases under 600°C annealing. For all samples, the coercivity of FePt increased as increasing annealing temperature. However, the coercivity decreased while annealing temperature higher than 650°C. A large perpendicular coercivity, namely 11000 and 9000 Oe, was obtained in 600°C annealed FePt samples grown on 20nm and 200nm pore diameter AAO templates with Au buffer layers, respectively, as shown in Figs. (a) and (b). It is in a good agreement with the observation of FePt L₁₀(001) phases. And a relative lower perpendicular coercive value, namely 6500 and 1000 Oe, was observed in FePt films directly grown on 20nm and 200nm pore diameter AAO templates, respectively, as shown in Figs. (c) and (d). That resulted from the interdiffusion between FePt and alumina. From these magnetic investigations, we concluded that a template with small pore diameter (or with large pore density) will enhance the coercive force (or domain wall pinning effect). In summary, we have observed experimentally the first time the structure and magnetism of FePt on AAO template. The Au (100) buffer layers and AAO templates will enhance the coercive force of FePt films through assisting the formation of L₁₀(001) phases and providing extra pinning sites, respectively.



[1] D. Weller et al., IEEE Trans. Magn. 36, 10 (2000).

[2] F. Y. Yang, K. Liu, K.M. Hong, D.H. Reich, P.C. Searson, C.L. Cien, Science 284, 1335 (1999).

ER12

Effects of SiN_x Content on the Microstructure and Magnetic Properties of FePt-SiN_x Granular Thin Films

Y. H. Fang^{1*}, P. C. Kuo¹, G. P. Lin¹, S. C. Chen², and K. T. Huang¹

¹Institute of Materials Science and Engineering, National Taiwan University, Taipei 10617, Taiwan

²Department of Materials Engineering, MingChi University of Technology, Taipei 243, Taiwan

*Corresponding author: Y. H. Fang, e-mail: d93527014@ntu.edu.tw

(FePt)_{1-y}(SiN_x)_y (y=0 ~ 63 vol.%) nanocomposite thin films are fabricated by dc and rf magnetron co-sputtering of Fe, Pt and SiN_x targets, then annealed at different temperatures and times. As the SiN_x content was increased from 0 vol.% to 63 vol.%, the behavior of the (FePt)_{1-y}(SiN_x)_y films could be separated into three sections. First, as the SiN_x content is smaller than 15 vol.%, the FePt particles begin to be isolated partially and the particle sizes are not uniform. Second, as the SiN_x content increases from 15 vol.% to 39 vol.%, the particle size distributions of FePt become more uniform. In these films, the SiN_x matrix will impede the reverse of the spin moments of FePt. Therefore the high out-of-plane coercivity (H_{c⊥}) and in-plane coercivity (H_{c∥}) of these films are due to pinning sites effect of SiN_x matrix. Third, as the SiN_x content is higher than 39 vol.%, the H_{c⊥} and H_{c∥} of (FePt)_{1-y}(SiN_x)_y films decrease rapidly as the SiN_x content is increased. From a field emission gun high resolution transmission electron microscope (FEG-TEM) images of (FePt)₃₇(SiN_x)₆₃ film (as shown in fig.1), it is found that some particles are smaller than 5 nm (The bright regions and the dark regions of figure 1 are SiN_x matrix and FePt grains, respectively). Some grains of this film may be smaller than D_p (minimal stable particle diameter) and cause the drastically decrease of H_c value. The H_{c⊥}, H_{c∥}, out-of-plane squareness (S_⊥), and in-plane squareness (S_∥) values of the (FePt)₃₇(SiN_x)₆₃ film are 6.5 kOe, 6.3 kOe, 0.75, and 0.45 respectively. And a uniform particle size distribution granular (FePt)₃₇(SiN_x)₆₃ film with an average particle size about 5 nm was obtained. This (FePt)₃₇(SiN_x)₆₃ film is a good candidate for application on high density perpendicular magnetic recording media.

This work was supported by the National Science Council and Ministry of Economic Affairs of Taiwan through the NSC 95-2221-E-002-119-MY3 and 95-EC-17-A-08-S1-0006 grants, respectively.




Fig. 1. FEG-TEM images of (FePt)₃₇(SiN_x)₆₃ films annealed at 700 °C for 30 minutes.